



KeraCell III

Electrolyte Supported Cells



Key features

- ESC based on zirconia substrates
- high power density
- robust concerning long term, redox and thermal cycling stability
- SOEC: suitable for electrolysis

Cell Type III


Anode	NiO/GDC
Cathode	LSCF
Electrolyte	stabilized zirconia (thickness 90 - 250 μm , depending on material)

Cell performance – electrolyte materials

Characteristics	Unit	3YSZ	8YSZ	YScSZ	6Sc1CeSZ	10Sc1CeSZ
Electrolyte thickness	[μm]	95	160	150	130	165
Current density (0.7 V)	[mA/cm^2]	390	630	650	710*	880*
Voltage (-500 mA/cm^2)	[V]	1.21*	1.11	1.10	1.09	1.05
Area specific resistance	[Ωcm^2]	0.58	0.36	0.35	0.32	0.26

* extrapolated value

KeraCell III - typical electrode performance



Important notes

The data presented in this leaflet are in accordance with the present state of our knowledge. All statements, technical information and recommendations herein are based on tests we believe to be reliable. The customer is thereby not absolved from carefully checking all supplies immediately on receipt. The recommendations made in this catalogue should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection there with. We reserve the right to alter product constants within the scope of technical process or new developments. The recommendations do not absolve the customer from the obligation of investigating the possibility of infringement of third parties right and, if necessary, clarifying the position. Sellers' and manufacturer' only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable either in tort or contract for any loss or damage, direct or incidental, or consequential, including loss of profits or revenue arising out of the use or the inability to use a product. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer.

27-06-2014