

## **GFU 15 silicone free**

**Gap Filler Liquid** 



- ◆ All applications with high fabrication tolerances
- Encapsulation
- Electric vehicles
- High energy rechargeable batteries

**Benefits** 

- Room temperature curing
- Liquid assembly

Properties	Unit	GFU 15
Colour		orange
Basic material		silicone free
Mixing ratio		1:1
Curing at room temperature	h	< 24 RT
Thermal Properties*		
Thermal resistance R <sub>th</sub>	K/W	1.6
Thermal conductivity λ	W/mK	1.5
Electrical Properties**		
Dielectric breakdown voltage U <sub>d; ac</sub>	kV	8
Mechanical Properties		
Hardness	Shore 00	65 - 85
Physical Properties		
Application temperature***	°C	-40 to 110
Density	g/cm³	2.30
Viscosity A Comp.****	Pas	140 - 180
Viscosity B Comp.****	Pas	140 - 180
Flame rating*****	UL-94	V-0
Possible thickness	mm	0.2 - 5.0
Thermal conductivity $\lambda$ Electrical Properties**  Dielectric breakdown voltage $U_{d;ac}$ Mechanical Properties  Hardness  Physical Properties  Application temperature***  Density  Viscosity A Comp.****  Viscosity B Comp.****  Flame rating*****	W/mK kV Shore 00  °C g/cm³ Pas Pas UL-94	1.5 8 65 - 85 -40 to 110 2.30 140 - 180 140 - 180 V-0

<sup>\*</sup> Measured @ thickness 1 mm \*\*\*\* Shear rate 4s-1 / 25°C

Ceramic filled, solvent free two component elastomer. Room temperature curing makes it suitable for wet in wet production.

## **Dispensing technology** as a service:

Consulting, development & production. As a specialist for dispensing technology, we offer consulting, development and production services for the application of thermal material to different heat sinks or to customized components.

## **Customer benefit**

- **⊗** A professional service-provider for dispensing production and technology
- **⊗** A more economical dispensing material compared to conventional thermal pastes and tapes
- **♥** A time-saving, easy assembly due to the prefabricated, ready dispensed components

Data for engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

<sup>\*\*</sup> Measured @ thickness 0.5 mm \*\*\*\*\* KERAFOL® test according to UL

<sup>\*\*\*</sup> may cause increase in hardness



## NOTE:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. KERAFOL® is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. All specifications are subject to change without notice. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded. In case KERAFOL® would be nevertheless held liable, on whatever legal ground, KERAFOL® liability will in no event exceed the amount of the concerned delivery. All KERAFOL® products are sold pursuant to the KERAFOL® Terms and Conditions of sale and delivery in effect from time to time, a copy of which will be furnished upon request.

11-2022